



Suitable for external uses.



The product can be pigmented.

## INTONACHINO FINE "400"

### Description of product

"Grassello Paste" with selected white grinded marble (400micron) for a "Venetian Intonachino" effect - medium thickness.

### Application Field

Medium thickness coating for interiors and exteriors.

### Product characteristics

INTONACHINO FINE "400" - interior and exterior granular finishing which permits to obtain, with more layers, the traditional "Venetian Intonachino" finishing effect with chiaroscuro shades. The product, thanks to its naturalness, can be coloured with pastel light colours of the Tintometric system Luxury&Lime. The accurate composition makes the product very resistant after application. The tradition of lime, produced with an advance technology, aims Bericalce towards the Environment Care and Green Division market.

The natural raw materials, accurately selected, give INTONACHINO FINE "400" a very high ecologic value: the dispersion of humidity avoids the growth of moulds and bacteriums, without using chemical additives. Non-flammable and low odour.

Technical data	
Name	Intonachino Fine "400"
Composition	"Dolomitic" Lime Putty (Grassello) minimum 12 month aged, grinded marble and additives for less than 5%
Aspect	Dense paste
Color	Natural White - White
Dilution	Ready to use (if needed a dilution in water 0-5%)
Quantity per layer	approx. 0,7 - 1 m <sup>2</sup> /kg
PH	13
Vapour permeability	SD ~ 0,04 m (DIN 52615)
Water absorption	w ~ 0,3 kg / (m <sup>2</sup> h0,5) (EN 1062-3:2001)
VOC class	VOC 0 g/l - wall paint and subcategory "L" max. value UE 2010 30g/l
Specific weight	1,75 Kg/l
Packaging	25 kg buckets
Storage	Keep in dry place with temperture min.5° ÷ 30°C max.
Notice	Protect the surfaces from rain in the first 24 ÷ 48 hours after application

# **INTONACHINO FINE "400"**

---

## **Instructions for use**

- Prepare the base with a specific Primer, ISOLANTE ACRILICO or levelling base like ISOLANTE ANCORANTE BERICO.
  - The colours of the tintometric system Luxury&Lime must be produced on Natural White base
  - Application with stainless steel trowel
  - \* Application of 1 or more coatings.
  - Base must be clean and dry, any unsubstantial parts, traces of oil or grease must be removed; plaster any irregularity of the base.
  - Each layer of the coloured product must always be refined with a NEW trowel/sponge, using CLEAN water
  - It's advisable to wait at least 12 hours before further coats to avoid marked shadows
  - The product must be applied with an uniform and constant method, alternating new trowel-sponge.
  - It's important that the product be of the correct consistence and dilution according to the temperature and absorption of the surface.
  - Temperature of application: 5° to 35°C
  - All lime-based products have a normal drying time according to the thickness but, the real hardness is obtained through carbonation which occurs on contact with the air.
- This process could last many months

## **Notes**

The present technical chart has been written by Bericalce's experts and the indicated technical and scientific information have been tested in our own workshop.

Any responsibility regarding the results are due only to the method and conditions used during application of the product.

These indications are a valid support for testing the quality of the product in each specific case.

**Date of issue 23.12.2015**

**Revision nr.1 05.10.2016**

## **BeriCalce ITALIA**

Via Odorico da Pordenone, 18

36100 Vicenza - ITALY

Phone (+39) 0444 929102

Fax (+39) 0444 929102

Skype: bericalce

info@bericalce.com

**bericalce.com**