



MARMORINO ANTICO "300"

ANTIQUÉ MARMORINO "300"

Description of product

"Grassello Paste" with selected coloured marble powders (300microns), for a prestigious satin or semi-shiny Venetian Marmorino finishing effect.

Application Field

This is an extra fine product for prestigious interior decoration, due to it's particular reflections which can be admired in the satin/semi-shiny finishing.

Product characteristics

MARMORINO ANTICO "300" is one of the best products for prestigious interior finishings and permits to obtain the classical Marmorino effect in only one product reducing its consumption. The colour shades can be personalized by using the colour scheme of the Tintometric system Luxury&Lime. The accurate mixture of selected micro-marble produces a stucco in paste, ready to use, which permits a vast range of application methods able to satisfy the most sophisticated decorating requests. The tradition of lime, produced with an advance technology, projects Bericalce towards the Environment Care and Green Division market. The natural raw materials, accurately selected, give MARMORINO ANTICO "300" a very high ecologic value: the dispersion of humidity avoids the growth of moulds and bacteriums, without using chemical additives. Non-flammable and low odour.

Technical data	
Name	Marmorino Antico "300"
Composition	"Dolomitic" Lime Putty (Grassello) minimum 12 month aged, marble powders and additives for less than 4%
Aspect	Dense paste
Color	Natural White
Dilution	Ready to use (if needed a dilution in water 0-5%)
Quantity per layer	approx. 1,8 - 2,2 m ² /kg
PH	13
Vapour permeability	SD - 0,045m (DIN 52615)
Water absorption	w - 0,35kg / (m ² h ^{0,5}) (EN1062-3:2001)
VOC class	VOC 5g/l - wall paint and subcategory "L" max.value UE2010 30g/l
Specific weight	1,65 kg/l
Packaging	5 - 25 kg buckets
Storage	Keep in dry place with temperture min.5° - 30°C max.
Notice	Protect the surfaces from rain in the first 24 - 48 hours from application

MARMORINO ANTICO "300"

Instructions for use

- Prepare the base with a specific Primer, Isolante Acrilico or levelling base like Isolante Ancorante Berico
 - Application with stainless steel trowel
 - Base must be clean and dry, any unsubstantial parts, traces of oil or grease must be removed; plaster any irregularity of the base
 - Application of 2 or more coatings. After spreading, the grade of brightness will be refined with spatola and/or special clothes. We suggest to apply the second layer after 4 hours to permit the first layer to dry correctly
 - It's important that the product be of the correct consistence and dilution according to the temperature and absorption of the surface
 - Temperature of application: 5° to 35°C
 - All lime-based products have a normal drying time according to the thickness but, the real hardness is obtained through carbonation which occurs on contact with the air
- This process could last many months

Notes

The present technical chart has been written by Bericalce's experts and the indicated technical and scientific information have been tested in our own workshop.

Any responsibility regarding the results are due only to the method and conditions used during application of the product.

These indications are a valid support for testing the quality of the product in each specific case.

Date of issue 01.04.2004

BeriCalce ITALIA

Via Odorico da Pordenone, 18

36100 Vicenza - ITALY

Phone (+39) 0444 929102

Fax (+39) 0444 929102

Skype: bericalce

info@bericalce.com

bericalce.com