



Suitable for external uses.



The product can be pigmented.

TECHNICAL CHART 139

ROCCIA VIVA

Description of product

Powder mixture composed of selected white marble powders, powdered resins, and hydraulic binders for prestigious high-thickness finishes with a rock effect.

Application Field

Prestigious, high-quality decorations for both interiors and exteriors.

Product characteristics

ROCCIA VIVA is a decorative coating for high-thickness finishes, suitable for creating rock-effect textures.

The color of the product can be customized with shades from the Luxury&Lime tinting system.

Its careful formulation makes the product easy to apply, allowing for a wide range of application methods to satisfy even the most sophisticated decorative requirements.

The carefully selected raw materials give ROCCIA VIVA extremely high breathability and strong resistance to mold, bacteria, and alkalis. The product is non-flammable and odorless.

Technical data	
Name	Roccia Viva
Composition	Hydraulic binders, marble powders, sands, and additives
Aspect	Powder
Color	Beige
Dilution	In water 20%
Quantity per layer	3-4 cm
PH	13 in water solution
Vapour permeability	SD ~ 0,04 m (DIN 52 615)
Water absorption	w ~ 0,3 kg / (m ² h0,5) (EN 1062-3:2001)
VOC class	VOC 0 g/l, wall paint and subcategory "L" max.value UE 2010 30g/
Packaging	25 Kg buckets
Storage	Keep in dry place with temperture min.5° - 30°C max.
Notice	Protect the surfaces from rain in the first 24 - 48 hours after application

ROCCIA VIVA

Instructions for use

- We recommend preparing the base with a specific primer such as ISOLANTE CONSOLIDANTE ACRILICO or with a leveling primer such as ISOLANTE ANCORANTE BERICO.
- Mix the product evenly with clean water.
- Apply with stainless steel/plastic decorative trowels.
- Check that the substrate is clean and dry, remove any loose parts, eliminate traces of oil and grease, and fill any irregularities in the substrate.
- The product should be applied in one or more coats.
- After applying one coat of the product, use a stainless steel/plastic trowel and decorative tools to create the rock effect.
- After 24 hours, the surface can be sanded to make it even smoother and more uniform.
- It is important that the material has the right consistency and dilution based on the temperature and absorption of the substrate.
- Application temperature 5° - 35°C

Notes

The present technical chart has been written by Bericalce's experts and the indicated technical and scientific information have been tested in our own workshop.

Any responsibility regarding the results are due only to the method and conditions used during application of the product.

These indications are a valid support for testing the quality of the product in each specific case.

Date of issue **17.11.2025**

Date of revision -

BeriCalce S.r.l.

ViaPiave, 23

36033 Isola Vicentina (VI) - ITALIA

Tel1. (+39) 0444 929102

Tel2. (+39) 0444 654919

Skype: bericalce

info@bericalce.com

bericalce.com