

ELITE TRAVERTINO

DECORATIVE MURAL FINISHING FOR EXTERIOR AND INTERIOR

PRODUCT PROPERTIES

ELITE TRAVERTINO is a powdered mural covering made of slaked lime, marble dust, hydraulic binders, inorganic pigments and particular additives that grant to the product the following characteristics:

GOOD TRASPIRABILITY, GOOD RESISTANCE to CHEMICAL-PHYSICAL and BIOLOGICAL AGGRESSIONS, GOOD UV RAYS RESISTANCE, PLEASANT SEMIGLOSS CHROMATIC EFFECT (ANCIENT MARBLE STYLE).

IDEAL USES

ELITE TRAVERTINO is ideal to decorate buildings of high artistic interest, both ancient and modern ones. It allows to reproduce the same aesthetic effect of the natural travertine stone, bringing out the classic marble veins.

ELITE TRAVERTINO can be applied on hydraulic binders based plasters and on mineral paints and coatings, provided they're dry and well gripped to the surface.

TECHNICAL CHARACTERISTICS

SPECIFIC WEIGHT OF THE MIXED PRODUCT:

1,72 ÷ 1,74 kg/l.

SPREAD RATE:

1,5 ÷ 2 kg/m².

APPEARANCE AND FINISH:

Semi-gloss appearance, typical travertine stone finish.

AVAILABLE GRAN SIZE:

Fine Grain size (cod.126A) - Medium Grain size (cod.126B).

WAY OF USE

PREPARATION OF THE SURFACE:

Old synthetic paints have to be removed in order to get the surface ready. In case of old or damaged plasters, it is recommended to remove all the damaged parts and then fix with the appropriate mortar.

In both cases, before ELITE TRAVERTINO application, it is necessary to apply one coat of PRIMER UNIFORMANTE A.S. properly diluted.

ON NEW OR WELL-SEASONED SURFACES (from at least 28 days): apply ELITE TRAVERTINO directly on the surface, without any primer.

When applied in interiors it is also possible to apply one coat of FONDO DAMASCATO in order to uniform the absorption of the surface.

APPLICATION:

Mix powdered ELITE TRAVERTINO with water until obtaining an homogeneous and thixotropic paste. Apply one first coat by the stainless steel trowel and a slight pressure, thus avoiding any smear and/or relief.

Once the product is dried (about 8-10 hours), apply a second coat and before the complete drying, roughen the surface by a big grain sized or medium grain-sized sponge roller or by pad and then "draw" the smooth parts by stainless steel trowel. After about 10 minutes scrape the surface horizontally to reach a smooth surface with marble like veins. It is recommended to damp the surface during the two following days. It is also possible to colour ELITE TRAVERTINO with a coat of LE VELATURE (siloxane paint) by a sponge trowel.

MIXING RATIO:

Mix 18 kg of powdered ELITE TRAVERTINO with about 7 litres of water.

DRYING AT 20°C AND 65% R.H. :

By touch 60-90 minutes, in depth about 24 hours at 20°C.

TIME BETWEEN COATS:

Wait at least 8-10 hours..

ENVIRONMENTAL CONDITIONS:

Do not apply the product at temperatures lower than +10°C or higher than +25°, if rain or strong winds are expected or on sundrenched surfaces.

WARNINGS:

For external applications it is necessary to protect ELITE TRAVERTINO with a siloxane waterproof product after 7 days.

TOOLS CLEANING:

With water immediately after use.

SALES PACKAGINGS: 1 x 18 kg.

AVAILABLE COLOURS: Cream.

CONSERVATION AND STORAGE:

Store the cans well sealed in a cool and dry place, far away from frost.

NOTES:

This document has been issued at the best of our technical and scientific expertise. Di Donato Spa does not take any responsibility for the results obtained when using this product, since the conditions and application procedures are not controllable by us. Therefore it is advisable to preliminary check the suitability of the product in accordance with the specific case.

