

TECHNICAL CHART 04

# GRASSELLO LUCIDO "SALE PEPE"

## SHINY "SALT-PEPPER" GRASSELLO



The product can be pigmented.

### Description of product

"Shiny Grasselto Paste" mixed with selected and very fine micaceous and marble elements for a finishing with Venetian Stucco, smooth/dotted effect.

### Application Field

Highly shiny prestigious dotted decorations for interiors.

### Product characteristics

GRASSELLO LUCIDO SALE PEPE already known as "Rasatura Calce" is proposed again in a new young and modern way. The colour shades can be personalized by using the colour scheme of the Tintometric system Luxury&Lime. The accurate mixture of selected micro-marble produces a stucco in paste, ready to use, which permits a vast range of application methods able to satisfy the most sophisticated decorating requests. The tradition of lime, produced with an advance technology, aims Bericalce towards the Environment Care and Green Division market. The natural raw materials, accurately selected, give GRASSELLO LUCIDO SALE PEPE a very high ecologic value: the dispersion of humidity avoids the growth of moulds and bacteriums, without using chemical additives. Non-flammable and low odour.

Technical data	
Name	Grasselto Lucido "Sale Pepe"
Composition	"Dolomitic" Lime Putty (Grasselto) minimum 12 month aged marble powders and additives for less than 4%
Aspect	Highly dense paste
Color	Natural dotted white
Dilution	Ready to use (if needed a dilution in water 0-5%)
Quantity per layer	approx. 3 - 4m <sup>2</sup> /kg
PH	13
Vapour permeability	SD - 0,04m (DIN 52615)
Water absorption	w - 0,3kg / (m <sup>2</sup> h0,5) (EN1062-3:2001)
VOC class	VOC 5g/l - wall paint and subcategory "L" max.value UE2010 30g/l
Specific weight	1,45 kg/l
Packaging	5 - 22,5 kg buckets
Storage	Keep in dry place with temperture min.5° - 30°C max.
Notice	Protect the surfaces from rain in the 12 hours from application

## **GRASSELLO LUCIDO "SALE PEPE"**

---

### **Instructions for use**

- Prepare the base with a specific Primer, Isolante Acrilico or smoothing base like Micro Primer Veneziano of Bericalce
- Application with stainless steel trowel
- Base must be clean and dry, any unsubstantial parts, traces of oil or grease must be removed; plaster any irregularity of the base.
- Apply 2 coats on a very smooth base (basic levelling plaster). The first coat will be spreaded equally, leaving the product to dry for at least 4 hours. The second coat must be spreaded very smoothly and at the right time of drying, it must be polished. An additional step will be done to refine the grade of brightness by using a trowel and/or special tools.
- Temperature of application: 5° to 35°C
- All lime-based products have a normal drying time according to the thickness but, the real hardness is obtained through carbonation which occurs on contact with the air.  
This process could last many months

### **Notes**

The present technical chart has been written by Bericalce's experts and the indicated technical and scientific information have been tested in our own workshop.

Any responsibility regarding the results are due only to the method and conditions used during application of the product.

These indications are a valid support for testing the quality of the product in each specific case.

**Date of issue 01.04.2004**

### **BeriCalce ITALIA**

Via Odorico da Pordenone, 18

36100 Vicenza - ITALY

Phone (+39) 0444 929102

Fax (+39) 0444 929102

Skype: bericalce

info@bericalce.com

**bericalce.com**